

CEPLASTER™

Cement Based Plaster

WALL MESH SYSTEM

PRODUCT DESCRIPTION

CEPLASTER™ is a cementitious ready mix plaster, to carry out plastering and rendering works in a clean and speedy manner, while keeping a homogeneous mix. Due to its high content in additives, it has a better shrinkage control as well as workability and curing. It can be applied by a suitable plastering machine or manually. CEPLASTER™ specially designed for FRCM composite system and WallMesh system.

FEATURES AND BENEFITS

- Ready to use, mix with water only
- Good adhesion and good mechanical properties
- Good workability
- Durable
- Traditional manual application
- Suitable plaster-spraying machines application
- Uniform and smooth finish
- Reduce Construction Costing

TECHNICAL DATA

TECHNICAL DATA		
	Unit	CEPLASTER™
Composition	-	Portland cement, selected sand, specific additives & fibers
Appearance / Colour	-	Grey Powder
Density	kg/l	1.50
28-day Tensile Adhesion Strength	kg/cm ²	14
28 day compressive strength	kg/cm ²	115
Mixing Ratio	-	16 L of water per 100 kg plaster
Pot Life (at 23 °C)	min	120

Where / When To Use

CEPLASTER™ cementitious ready mix plaster is recommended for:

- Wall Stabilization using WallMesh system
- Structural strengthening using FRCM system

APPLICATION INSTRUCTIONS

▪ MIXING

Add water according to the desired consistency and recommended mixing ratio into a clean mixing vessel before slowly adding the CEPLASTER™ cement based plaster.

▪ APPLICATION

The plaster is now ready for application by machine or manually with a plastering trowel. Apply the plaster on the prepared surface at a thickness between 10 and 20 mm in one layer.

STORAGE

Store the product in dry conditions in original sealed undamaged packaging at temperatures between +5 °C and +35 °C. Protect from direct sunlight, heat and moisture

SHELF LIFE

12 months from date of production.



DISCLAIMER: All guidelines, recommendations, statements, and technical data contained herein are based on information and tests we believe to be reliable and correct, but accuracy and completeness of said tests are not guaranteed and are not to be construed as a warranty, either expressed or implied. It is the user's responsibility to satisfy himself, by his own information and test, to determine suitability of the product for his own intended use, application and job situation and user assumes all risk and liability resulting from his use of the product. We do not suggest or guarantee that any hazard listed herein are the only ones which may exist. Neither seller nor manufacturer shall be liable to the buyer or any third person for any injury, loss or damage directly or indirectly resulting from use of, or inability to use, the product. Recommendations or statements, whether in writing or oral, other than those contained herein shall not be binding upon the manufacturer, unless in writing and signed by a corporate officer of the manufacturer. Technical and application information is provided for the purpose of establishing a general profile of the material and proper application procedures. Test performance results were obtained in a controlled environment and Wallpostmesh products makes no claim that these tests or any other tests, accurately represent all environments.

